

GENERAL INFORMATION
General information

Typology	Master alloy for gold
Color	Yellow
Color shade	Rich yellow
Production process	All-purpose
Grain refinement level	Medium
Deoxidation level	Minimum

Commercial composition (%)

CU	51.0
AG	47.0
ZN	2.0

Melting Temperatures

Solidus [°C]	880.0
Liquidus [°C]	895.0
Melting range [°C]	15.0

FULL CHARACTERIZATION DATA
Color coordinates

L *	a*	b*	c*	Yellow Index
84.3	4.4	21.4	21.8	

Mechanical characteristics

As cast hardness [HV 0.2]	160.0
Hardness after 70% area red. [HV 0.2]	250.0
Hardness after annealing [HV 0.2]	160.0
Single step age-hardening hardness [HV 0.2]	240.0
Tensile strength (Rm) [Mpa]	455.0
Yield strength (Rp0.2) [MPa]	290.0
Elongation at rupture (A) [%]	39.0

Physical characteristics

Density [g/cm ³]	15.2
------------------------------	------

General characteristics

As cast grain size [μm]	200.0
-------------------------	-------

Product applications

Continuous casting
 Ingot casting
 Handmade production
 Massive chain production
 Wire production
 Sheet production
 Stamping production
 Blanking production

CASTING PROCESSING PARAMETERS
Pre-melting temperature

Temperature [°C] 1015

POURING TEMPERATURES	Flask from [°C]	Flask to [°C]	Metal from [°C]	Metal to [°C]
< 0.5 mm	670	720	1000	1030
0.5 - 1.2 mm	580	650	980	1000
> 1.2 mm	460	600	960	980

Trees without stones

Let the flask cool down for 10-15 minutes, then quench it in water.

Pickling

Dip in RADIAL solution (50 g/l conc. at 60°C) for 2 minutes, or in sulphuric acid (10% concentration at 50°C) for 5 minutes.

MECHANICAL WORKING PARAMETERS
Pre-melting temperature

Temperature [°C] 1015

Reductions

Wire - diameter (%)	45.0
Sheet - area or thickness (%)	70.0

POURING TEMPERATURES	Countinous from [°C]	Countinous to [°C]	Ingot to [°C]	Ingot from [°C]
Temperatures	995	1075	975	1015

MECHANICAL WORKING ANNEALING

	Temp. from [°C]	Temp. to [°C]	Time [min]
< 1 mm	600	640	25
1 - 5 mm	600	640	30
> 5 mm	600	640	35

Mechanical working quenching

Quench directly in 50%/50% water/alcohol solution or in water.

OG605B 750‰

ALL-PURPOSE MASTER ALLOY FOR 750‰ (18 KT) YELLOW GOLD

AGE HARDENING PROCESSING PARAMETERS

SINGLE STEP	Temperature [°C]	Time [min]	Quenching
AGE HARDENING	275.0	90.0	In air or in furnace